



Bondall PTY LTD
ACN: 008 734 996
ABN: 27 008 734 996

113 Belmont Ave
Belmont WA 6104

PO Box 111
Cloverdale WA 6985

P: 08 9277 8844
F: 08 9277 4068

bondall@bondall.com
www.bondall.com

BONDALL – MONOCEL DECKING OIL

REVISED: APRIL 2005

DESCRIPTION

Triple Protection – UV protection, Water protection and Fungal protection

Bondall Monocel Decking Oil is a high performance, UV enhanced, naturally pigmented enriching oil finish providing maximum exterior durability for timber decking. The formulation protects timber from exterior conditions, highlighting the natural beauty and extending the life of your timber decking, patio or porch.

Note: Monocel Decking Oil is not recommended for use on rough sawn timbers.

SURFACE PREPARATION

- Surface preparation is important. All surfaces should be dry, finely sanded and free from dust, grease, grime, wax, oil, mildew, fungi and algae. Any previously applied paint, varnish, shellac etc, must be removed before coating.
- Allow all new decking to age and weather for at least 6-8 weeks prior to applying Monocel Decking Oil. Wash down frequently with water during this period. This will assist in leaching out the tannins in the timber. If new decking is not weathered an uneven or blotchy finish may result.

IMPORTANT: To allow proper penetration, some timber such as Merbau, may require additional weathering and/or cleaning. Allow to dry thoroughly before coating.

APPLICATION

- Stir well before and during use. **DO NOT SHAKE CAN.** Use a 25mm broad timber or metal paddle and stir for 5 min. Apply Monocel Decking Oil with a good quality soft, clean paintbrush, applicator pad, short nap roller or by low pressure spray. If large areas are to be coated we recommend the use of a short nap mohair roller to assist with application.
- The first coat should be allowed to dry for a minimum of 4 hours before lightly sanding the surface with 240 grit sandpaper. Thoroughly dust the surface (a tack rag is recommended).
- Application of 2 coats is recommended for best results. On dense / oily timbers 1 coat may be sufficient. Timber should be tested to determine the suitable number of coats. Monocel Decking Oil should not be applied over painted surfaces. Reapply as timber changes colour or decreased water repellency is observed.
- Do not apply if the temperature is below 10°C or if rain is expected within 24 hours.
- Ensure adequate ventilation during use.

COVERAGE

Approximately 17 square metres per Litre depending on texture and porosity of surface.

DRYING TIME

Monocel Decking Oil will be touch dry in 4 hours but it is recommended that the product be left a minimum 24 hours before recoating. Drying times are a guide only. Longer drying times may be required in cooler or humid conditions.



Wholly Australian Owned & Manufactured

the solution  bondall





Bondall PTY LTD
ACN: 008 734 996
ABN: 27 008 734 996

113 Belmont Ave
Belmont WA 6104

PO Box 111
Cloverdale WA 6985

P: 08 9277 6844
F: 08 9277 4068

bondall@bondall.com
www.bondall.com

CLEAN UP

- Clean rim and tightly close lid.
- Clean all equipment promptly with mineral turpentine.
- Rinse thoroughly with fresh water and a little detergent.
- Please dispose of any waste materials responsibly.
- Do not pour excess product or washings down drains or sinks.
- Keep unwanted product in sealed container and use appropriate waste disposal services.

SIZES

4 & 10 Litre containers

PRECAUTION/FIRST AID

- Wear protective clothing (eg coveralls, impervious gloves, goggles).
- Avoid contact with eyes or skin.
- Avoid inhalation and ensure good ventilation during use.
- If spraying, use suitable respirator.
- Seal container when not in use.
- Keep out of reach of children.
- If accidental poisoning occurs, seek urgent medical advice or contact the Poisons Information Centre on 13 11 26.

Material Safety Data information is available on request.

DISCLAIMER

The information contained here is given in good faith and is intended to be of assistance to users. The performance of this product is dependant upon its correct preparation, application onto a sound surface and attention to the instructions on the label. The wide variety of surface conditions makes it impossible for the company to assume liability for any loss, consequential or otherwise, arising from the use of this product. Should the product be found defective our liability shall be limited to the replacement of the product only. We reserve the right to amend specifications and application techniques without prior notice.

For further advice please contact the Bondall Building and Renovating Service on 1800 810 123 or (08) 9277 6844



Wholly Australian Owned & Manufactured

the solution  bondall

